

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-134878

(43)Date of publication of application : 20.05.1997

(51)Int.Cl.

H01L 21/203
C30B 29/38
H01L 21/205
H01L 33/00
H01S 3/18

(21)Application number : 07-292320

(71)Applicant : MATSUSHITA ELECTRON CORP

(22)Date of filing : 10.11.1995


(72)Inventor : KONDO OSAMU
HASHIMOTO TADAAKI
KUME MASAHIRO

(54) MANUFACTURE OF GALLIUM NITRIDE COMPOUND SEMICONDUCTOR

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a method by which a high-quality GaN compound semiconductor crystal having a low dislocation density can be grown.

SOLUTION: A Ga thin film 12 having a thickness of about 50nm or thinner is formed on a silicon substrate 11 by a molecular beam growing method. Then a nitride layer 13 is formed on the film 12 by using the metal organic chemical vapor deposition(MOCVD) method and a GaN crystal is grown on the layer 13 by using the MOCVD method. Since the lattice defect caused by lattice unmatched, the thermal strain caused by the difference in coefficient of thermal expansion, and the surface energy are relieved by the function of the liquid Ga thin film 12, the GaN crystal is grown in two-dimensional directions and a GaN crystal having such a low dislocation density as about 10^5cm^{-2} is obtained. It is also possible to directly grow a compound semiconductor crystal of a gallium nitride, such as GaN, etc., on the Ga thin film without forming the nitride layer 13.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of
rejection]

[Date of requesting appeal against examiner's decision of
rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office